

Rounds

Half Rounds

<i>MATERIAL</i>	<i>GRADE</i>	<i>TYPE</i>	<i>SIZE</i> <i>(In Inches)</i>	<i>WEIGHT/FT</i> <i>(Pounds per Foot)</i>	<i>BAR WEIGHT</i> <i>(Pounds per 20' Bar)</i>	<i>BAR WEIGHT</i> <i>(Pounds per 12' Bar)</i>
Carbon Steel	A.S.T.M. A-36	Hot Rolled	1/2	3.338	6.676	
Carbon Steel	A.S.T.M. A-36	Hot Rolled	3/4	.7510	15.02	
Carbon Steel	A.S.T.M. A-36	Hot Rolled	5/8	.5216	10.43	
Carbon Steel	A.S.T.M. A-36	Hot Rolled	1	1.335	26.70	

Rounds

<i>MATERIAL</i>	<i>GRADE</i>	<i>TYPE</i>	<i>SIZE</i> <i>(In Inches)</i>	<i>WEIGHT/FT</i> <i>(Pounds per Foot)</i>	<i>BAR WEIGHT</i> <i>(Pounds per 20' Bar)</i>	<i>BAR WEIGHT</i> <i>(Pounds per 12' Bar)</i>
Aluminum	Type 2011-T3		1/8	.0150		.1800
Aluminum	Type 2011-T3		5/32	.0235		.2820
Aluminum	Type 2011-T3		3/16	.0338		.4056
Aluminum	Type 2011-T3		7/32	.0460		.5520
Aluminum	Type 2011-T3		1/4	.0601		.7212
Aluminum	Type 2011-T3		9/32	.0761		.9132
Aluminum	Type 2011-T3		5/16	.0939		1.127
Aluminum	Type 2011-T3		11/32	.1136		1.363

Aluminum	Type 2011-T3	3/8	.1352	1.622
Aluminum	Type 2011-T3	13/32	.1587	1.904
Aluminum	Type 2011-T3	7/16	.1840	2.208
Aluminum	Type 2011-T3	15/32	.2113	2.536
Aluminum	Type 2011-T3	1/2	.2403	2.884
Aluminum	Type 2011-T3	17/32	.2714	3.257
Aluminum	Type 2011-T3	9/16	.3042	3.650
Aluminum	Type 2011-T3	19/32	.3390	4.068
Aluminum	Type 2011-T3	5/8	.3755	4.506
Aluminum	Type 2011-T3	21/32	.4141	4.969
Aluminum	Type 2011-T3	11/16	.4544	5.453
Aluminum	Type 2011-T3	3/4	.5407	6.488
Aluminum	Type 2011-T3	13/16	.6346	7.615
Aluminum	Type 2011-T3	7/8	.7360	8.832
Aluminum	Type 2011-T3	15/16	.8449	10.14
Aluminum	Type 2011-T3	1	.9613	11.54
Aluminum	Type 2011-T3	1 1/16	1.085	13.02
Aluminum	Type 2011-T3	1 1/8	1.217	14.60
Aluminum	Type 2011-T3	1 3/16	1.356	16.27
Aluminum	Type 2011-T3	1 1/4	1.502	18.02
Aluminum	Type 2011-T3	1 5/16	1.656	19.87
Aluminum	Type 2011-T3	1 3/8	1.818	21.82

Aluminum	Type 2011-T3	1 7/16	1.986	23.83
Aluminum	Type 2011-T3	1 1/2	2.163	25.96
Aluminum	Type 2011-T3	1 9/16	2.347	28.16
Aluminum	Type 2011-T3	1 5/8	2.538	30.46
Aluminum	Type 2011-T3	1 3/4	2.944	35.33
Aluminum	Type 2011-T3	1 7/8	3.380	40.56
Aluminum	Type 2011-T3	2	3.845	46.14
Aluminum	Type 2011-T3	2 1/8	4.341	52.09
Aluminum	Type 2011-T3	2 1/4	4.867	58.40
Aluminum	Type 2011-T3	2 3/8	5.422	65.06
Aluminum	Type 2011-T3	2 1/2	6.008	72.10
Aluminum	Type 2011-T3	2 3/4	7.270	87.24
Aluminum	Type 2011-T3	3	8.652	103.80
Aluminum	Type 2017-T4	1/8	.0150	.1800
Aluminum	Type 2017-T4	5/32	.0235	.2820
Aluminum	Type 2017-T4	3/16	.0338	.4056
Aluminum	Type 2017-T4	7/32	.0460	.5520
Aluminum	Type 2017-T4	1/4	.0601	.7212
Aluminum	Type 2017-T4	9/32	.0761	.9132
Aluminum	Type 2017-T4	5/16	.0939	1.127
Aluminum	Type 2017-T4	3/8	.1352	1.622
Aluminum	Type 2017-T4	7/16	.1840	2.208

Aluminum	Type 2017-T4	1/2	.2403	2.884
Aluminum	Type 2017-T4	9/16	.3042	3.650
Aluminum	Type 2017-T4	5/8	.3755	4.506
Aluminum	Type 2017-T4	11/16	.4544	5.453
Aluminum	Type 2017-T4	3/4	.5407	6.488
Aluminum	Type 2017-T4	13/16	.6346	7.615
Aluminum	Type 2017-T4	7/8	.7360	8.832
Aluminum	Type 2017-T4	15/16	.8449	10.14
Aluminum	Type 2017-T4	1	.9613	11.54
Aluminum	Type 2017-T4	1 1/16	1.085	13.02
Aluminum	Type 2017-T4	1 1/8	1.217	14.60
Aluminum	Type 2017-T4	1 3/16	1.356	16.27
Aluminum	Type 2017-T4	1 1/4	1.502	18.02
Aluminum	Type 2017-T4	1 5/16	1.656	19.87
Aluminum	Type 2017-T4	1 3/8	1.818	21.82
Aluminum	Type 2017-T4	1 7/16	1.986	23.83
Aluminum	Type 2017-T4	1 1/2	2.163	25.96
Aluminum	Type 2017-T4	1 9/16	2.347	28.16
Aluminum	Type 2017-T4	1 5/8	2.538	30.46
Aluminum	Type 2017-T4	1 11/16	2.738	32.86
Aluminum	Type 2017-T4	1 3/4	2.944	35.33
Aluminum	Type 2017-T4	1 13/16	3.158	37.90

Aluminum	Type 2017-T4	1 7/8	3.380	40.56
Aluminum	Type 2017-T4	1 15/16	3.609	43.31
Aluminum	Type 2017-T4	2	3.845	46.14
Aluminum	Type 2017-T4	2 1/16	4.092	49.10
Aluminum	Type 2017-T4	2 1/8	4.341	52.09
Aluminum	Type 2017-T4	2 1/4	4.867	58.40
Aluminum	Type 2017-T4	2 5/16	5.141	61.69
Aluminum	Type 2017-T4	2 3/8	5.422	65.06
Aluminum	Type 2017-T4	2 1/2	6.008	72.10
Aluminum	Type 2017-T4	2 9/16	6.312	75.74
Aluminum	Type 2017-T4	2 5/8	6.624	79.49
Aluminum	Type 2017-T4	2 3/4	7.270	87.24
Aluminum	Type 2017-T4	3	8.652	103.80
Aluminum	Type 2017-T4	3 1/8	8.652	103.80
Aluminum	Type 2017-T4	3 1/4	10.15	121.80
Aluminum	Type 2017-T451	1/8	.0150	.1800
Aluminum	Type 2017-T451	5/32	.0235	.2820
Aluminum	Type 2017-T451	3/16	.0338	.4056
Aluminum	Type 2017-T451	7/32	.0460	.5520
Aluminum	Type 2017-T451	1/4	.0601	.7212
Aluminum	Type 2017-T451	9/32	.0761	.9132
Aluminum	Type 2017-T451	5/16	.0939	1.127

Aluminum	Type 2017-T451	3/8	.1352	1.622
Aluminum	Type 2017-T451	7/16	.1840	2.208
Aluminum	Type 2017-T451	1/2	.2403	2.884
Aluminum	Type 2017-T451	9/16	.3042	3.650
Aluminum	Type 2017-T451	5/8	.3755	4.506
Aluminum	Type 2017-T451	11/16	.4544	5.453
Aluminum	Type 2017-T451	3/4	.5407	6.488
Aluminum	Type 2017-T451	13/16	.6346	7.615
Aluminum	Type 2017-T451	7/8	.7360	8.832
Aluminum	Type 2017-T451	15/16	.8449	10.14
Aluminum	Type 2017-T451	1	.9613	11.54
Aluminum	Type 2017-T451	1 1/16	1.085	13.02
Aluminum	Type 2017-T451	1 1/8	1.217	14.60
Aluminum	Type 2017-T451	1 3/16	1.356	16.27
Aluminum	Type 2017-T451	1 1/4	1.502	18.02
Aluminum	Type 2017-T451	1 5/16	1.656	19.87
Aluminum	Type 2017-T451	1 3/8	1.818	21.82
Aluminum	Type 2017-T451	1 7/16	1.986	23.83
Aluminum	Type 2017-T451	1 1/2	2.163	25.96
Aluminum	Type 2017-T451	1 9/16	2.347	28.16
Aluminum	Type 2017-T451	1 5/8	2.538	30.46
Aluminum	Type 2017-T451	1 11/16	2.738	32.86

Aluminum	Type 2017-T451	1 3/4	2.944	35.33
Aluminum	Type 2017-T451	1 13/16	3.158	37.90
Aluminum	Type 2017-T451	1 7/8	3.380	40.56
Aluminum	Type 2017-T451	1 15/16	3.609	43.31
Aluminum	Type 2017-T451	2	3.845	46.14
Aluminum	Type 2017-T451	2 1/16	4.092	49.10
Aluminum	Type 2017-T451	2 1/8	4.341	52.09
Aluminum	Type 2017-T451	2 1/4	4.867	58.40
Aluminum	Type 2017-T451	2 5/16	5.141	61.69
Aluminum	Type 2017-T451	2 3/8	5.422	65.06
Aluminum	Type 2017-T451	2 1/2	6.008	72.10
Aluminum	Type 2017-T451	2 9/16	6.312	75.74
Aluminum	Type 2017-T451	2 5/8	6.624	79.49
Aluminum	Type 2017-T451	2 3/4	7.270	87.24
Aluminum	Type 2017-T451	3	8.652	103.80
Aluminum	Type 2017-T451	3 1/8	8.652	103.80
Aluminum	Type 2017-T451	3 1/4	10.15	121.80
Aluminum	Type 2024-T351	1/8	.0150	.1800
Aluminum	Type 2024-T351	3/16	.0338	.4056
Aluminum	Type 2024-T351	1/4	.0601	.7212
Aluminum	Type 2024-T351	5/16	.0939	1.127
Aluminum	Type 2024-T351	3/8	.1352	1.622

Aluminum	Type 2024-T351	7/16	.1840	2.208
Aluminum	Type 2024-T351	1/2	.2403	2.884
Aluminum	Type 2024-T351	9/16	.3042	3.650
Aluminum	Type 2024-T351	5/8	.3755	4.506
Aluminum	Type 2024-T351	11/16	.4544	5.453
Aluminum	Type 2024-T351	3/4	.5407	6.488
Aluminum	Type 2024-T351	13/16	.6346	7.615
Aluminum	Type 2024-T351	7/8	.7360	8.832
Aluminum	Type 2024-T351	15/16	.8449	10.14
Aluminum	Type 2024-T351	1	.9613	11.54
Aluminum	Type 2024-T351	1 1/16	1.085	13.02
Aluminum	Type 2024-T351	1 1/8	1.217	14.60
Aluminum	Type 2024-T351	1 1/4	1.502	18.02
Aluminum	Type 2024-T351	1 5/16	1.656	19.87
Aluminum	Type 2024-T351	1 3/8	1.818	21.82
Aluminum	Type 2024-T351	1 1/2	2.163	25.96
Aluminum	Type 2024-T351	1 9/16	2.347	28.16
Aluminum	Type 2024-T351	1 5/8	2.538	30.46
Aluminum	Type 2024-T351	1 3/4	2.944	35.33
Aluminum	Type 2024-T351	1 7/8	3.380	40.56
Aluminum	Type 2024-T351	2	3.845	46.14
Aluminum	Type 2024-T351	2 1/8	4.341	52.09

Aluminum	Type 2024-T351	2 1/4	4.867	58.40
Aluminum	Type 2024-T351	2 3/8	5.422	65.06
Aluminum	Type 2024-T351	2 1/2	6.008	72.10
Aluminum	Type 2024-T351	2 5/8	6.624	79.49
Aluminum	Type 2024-T351	2 3/4	7.270	87.24
Aluminum	Type 2024-T351	3	8.652	103.80
Aluminum	Type 2024-T351	3 1/8	8.652	103.80
Aluminum	Type 2024-T351	3 1/4	10.15	121.80
Aluminum	Type 2024-T351	3 3/8	10.84	130.10
Aluminum	Type 2024-T351	3 1/2	11.66	139.90
Aluminum	Type 2024-T351	3 3/4	13.39	160.70
Aluminum	Type 2024-T351	4	15.23	182.80
Aluminum	Type 2024-T351	4 1/4	17.19	206.30
Aluminum	Type 2024-T351	4 1/2	19.28	231.40
Aluminum	Type 2024-T351	4 3/4	21.48	257.80
Aluminum	Type 2024-T351	5	23.80	285.60
Aluminum	Type 2024-T351	5 1/4	26.24	314.90
Aluminum	Type 2024-T351	5 1/2	28.80	345.60
Aluminum	Type 2024-T351	6	34.27	411.20
Aluminum	Type 2024-T351	6 1/2	40.22	482.60
Aluminum	Type 2024-T4	1/8	.0150	.1800
Aluminum	Type 2024-T4	3/16	.0338	.4056

Aluminum	Type 2024-T4	1/4	.0601	.7212
Aluminum	Type 2024-T4	5/16	.0939	1.127
Aluminum	Type 2024-T4	3/8	.1352	1.622
Aluminum	Type 2024-T4	7/16	.1840	2.208
Aluminum	Type 2024-T4	1/2	.2403	2.884
Aluminum	Type 2024-T4	9/16	.3042	3.650
Aluminum	Type 2024-T4	5/8	.3755	4.506
Aluminum	Type 2024-T4	11/16	.4544	5.453
Aluminum	Type 2024-T4	3/4	.5407	6.488
Aluminum	Type 2024-T4	13/16	.6346	7.615
Aluminum	Type 2024-T4	7/8	.7360	8.832
Aluminum	Type 2024-T4	15/16	.8449	10.14
Aluminum	Type 2024-T4	1	.9613	11.54
Aluminum	Type 2024-T4	1 1/16	1.085	13.02
Aluminum	Type 2024-T4	1 1/8	1.217	14.60
Aluminum	Type 2024-T4	1 1/4	1.502	18.02
Aluminum	Type 2024-T4	1 5/16	1.656	19.87
Aluminum	Type 2024-T4	1 3/8	1.818	21.82
Aluminum	Type 2024-T4	1 1/2	2.163	25.96
Aluminum	Type 2024-T4	1 9/16	2.347	28.16
Aluminum	Type 2024-T4	1 5/8	2.538	30.46
Aluminum	Type 2024-T4	1 3/4	2.944	35.33

Aluminum	Type 2024-T4	1 7/8	3.380	40.56
Aluminum	Type 2024-T4	2	3.845	46.14
Aluminum	Type 2024-T4	2 1/8	4.341	52.09
Aluminum	Type 2024-T4	2 1/4	4.867	58.40
Aluminum	Type 2024-T4	2 3/8	5.422	65.06
Aluminum	Type 2024-T4	2 1/2	6.008	72.10
Aluminum	Type 2024-T4	2 5/8	6.624	79.49
Aluminum	Type 2024-T4	2 3/4	7.270	87.24
Aluminum	Type 2024-T4	3	8.652	103.80
Aluminum	Type 2024-T4	3 1/8	8.652	103.80
Aluminum	Type 2024-T4	3 1/4	10.15	121.80
Aluminum	Type 2024-T4	3 3/8	10.84	130.10
Aluminum	Type 2024-T4	3 1/2	11.66	139.90
Aluminum	Type 2024-T4	3 3/4	13.39	160.70
Aluminum	Type 2024-T4	4	15.23	182.80
Aluminum	Type 2024-T4	4 1/4	17.19	206.30
Aluminum	Type 2024-T4	4 1/2	19.28	231.40
Aluminum	Type 2024-T4	4 3/4	21.48	257.80
Aluminum	Type 2024-T4	5	23.80	285.60
Aluminum	Type 2024-T4	5 1/4	26.24	314.90
Aluminum	Type 2024-T4	5 1/2	28.80	345.60
Aluminum	Type 2024-T4	6	34.27	411.20

Aluminum	Type 2024-T4	6 1/2	40.22	482.60
Aluminum	Type 6061-T6	1/4	.0601	.7212
Aluminum	Type 6061-T6	5/16	.0939	1.127
Aluminum	Type 6061-T6	3/8	.1352	1.622
Aluminum	Type 6061-T6	7/16	.1840	2.208
Aluminum	Type 6061-T6	1/2	.2403	2.884
Aluminum	Type 6061-T6	9/16	.3042	3.650
Aluminum	Type 6061-T6	5/8	.3755	4.506
Aluminum	Type 6061-T6	3/4	.5407	6.488
Aluminum	Type 6061-T6	7/8	.7360	8.832
Aluminum	Type 6061-T6	1	.9613	11.54
Aluminum	Type 6061-T6	1 1/8	1.217	14.60
Aluminum	Type 6061-T6	1 1/4	1.502	18.02
Aluminum	Type 6061-T6	1 3/8	1.818	21.82
Aluminum	Type 6061-T6	1 1/2	2.163	25.96
Aluminum	Type 6061-T6	1 5/8	2.538	30.46
Aluminum	Type 6061-T6	1 3/4	2.944	35.33
Aluminum	Type 6061-T6	1 7/8	3.380	40.56
Aluminum	Type 6061-T6	2	3.845	46.14
Aluminum	Type 6061-T6	2 1/4	4.867	58.40
Aluminum	Type 6061-T6	2 1/2	6.008	72.10
Aluminum	Type 6061-T6	2 3/4	7.270	87.24

Aluminum	Type 6061-T6	3	8.652	103.80
Aluminum	Type 6061-T6	3 1/4	10.15	121.80
Aluminum	Type 6061-T6	3 1/2	11.66	139.90
Aluminum	Type 6061-T6	3 3/4	13.39	160.70
Aluminum	Type 6061-T6	4	15.23	182.80
Aluminum	Type 6061-T6	4 1/2	19.28	231.40
Aluminum	Type 6061-T6	5	23.80	285.60
Aluminum	Type 6061-T6	5 1/2	28.80	345.60
Aluminum	Type 6061-T6	6	34.27	411.20
Aluminum	Type 6061-T6	6 1/2	40.22	482.60
Aluminum	Type 6061-T651	1/4	.0601	.7212
Aluminum	Type 6061-T651	5/16	.0939	1.127
Aluminum	Type 6061-T651	3/8	.1352	1.622
Aluminum	Type 6061-T651	7/16	.1840	2.208
Aluminum	Type 6061-T651	1/2	.2403	2.884
Aluminum	Type 6061-T651	9/16	.3042	3.650
Aluminum	Type 6061-T651	5/8	.3755	4.506
Aluminum	Type 6061-T651	3/4	.5407	6.488
Aluminum	Type 6061-T651	7/8	.7360	8.832
Aluminum	Type 6061-T651	1	.9613	11.54
Aluminum	Type 6061-T651	1 1/8	1.217	14.60
Aluminum	Type 6061-T651	1 1/4	1.502	18.02

Aluminum	Type 6061-T651		1 3/8	1.818	21.82
Aluminum	Type 6061-T651		1 1/2	2.163	25.96
Aluminum	Type 6061-T651		1 5/8	2.538	30.46
Aluminum	Type 6061-T651		1 3/4	2.944	35.33
Aluminum	Type 6061-T651		1 7/8	3.380	40.56
Aluminum	Type 6061-T651		2	3.845	46.14
Aluminum	Type 6061-T651		2 1/4	4.867	58.40
Aluminum	Type 6061-T651		2 1/2	6.008	72.10
Aluminum	Type 6061-T651		2 3/4	7.270	87.24
Aluminum	Type 6061-T651		3	8.652	103.80
Aluminum	Type 6061-T651		3 1/4	10.15	121.80
Aluminum	Type 6061-T651		3 1/2	11.66	139.90
Aluminum	Type 6061-T651		3 3/4	13.39	160.70
Aluminum	Type 6061-T651		4	15.23	182.80
Aluminum	Type 6061-T651		4 1/2	19.28	231.40
Aluminum	Type 6061-T651		5	23.80	285.60
Aluminum	Type 6061-T651		5 1/2	28.80	345.60
Aluminum	Type 6061-T651		6	34.27	411.20
Aluminum	Type 6061-T651		6 1/2	40.22	482.60
Carbon Steel	AISI 1018	Cold Finished	1/8	.042	.504
Carbon Steel	AISI 1018	Cold Finished	5/32	0.65	.780
Carbon Steel	AISI 1018	Cold Finished	3/16	.094	1.128

Carbon Steel	AISI 1018	Cold Finished	7/32	.128	1.536
Carbon Steel	AISI 1018	Cold Finished	1/4	.167	2.004
Carbon Steel	AISI 1018	Cold Finished	9/32	.211	2.532
Carbon Steel	AISI 1018	Cold Finished	5/16	.261	3.132
Carbon Steel	AISI 1018	Cold Finished	11/32	.316	3.792
Carbon Steel	AISI 1018	Cold Finished	3/8	.376	4.512
Carbon Steel	AISI 1018	Cold Finished	13/32	.441	5.292
Carbon Steel	AISI 1018	Cold Finished	7/16	.511	6.132
Carbon Steel	AISI 1018	Cold Finished	15/32	.587	7.044
Carbon Steel	AISI 1018	Cold Finished	1/2	.668	8.016
Carbon Steel	AISI 1018	Cold Finished	17/32	.754	9.048
Carbon Steel	AISI 1018	Cold Finished	9/16	.845	10.14
Carbon Steel	AISI 1018	Cold Finished	19/32	.941	11.29
Carbon Steel	AISI 1018	Cold Finished	5/8	1.04	12.48
Carbon Steel	AISI 1018	Cold Finished	11/16	1.26	15.12
Carbon Steel	AISI 1018	Cold Finished	3/4	1.50	18.00
Carbon Steel	AISI 1018	Cold Finished	13/16	1.76	21.12
Carbon Steel	AISI 1018	Cold Finished	7/8	2.04	24.48
Carbon Steel	AISI 1018	Cold Finished	15/16	2.35	28.20
Carbon Steel	AISI 1018	Cold Finished	1	2.67	32.04
Carbon Steel	AISI 1018	Cold Finished	1 1/16	3.01	36.12
Carbon Steel	AISI 1018	Cold Finished	1 1/8	3.38	40.56

Carbon Steel	AISI 1018	Cold Finished	1 3/16	3.77		45.24
Carbon Steel	AISI 1018	Cold Finished	1 1/4	4.17		50.04
Carbon Steel	AISI 1018	Cold Finished	1 5/16	4.60		55.20
Carbon Steel	AISI 1018	Cold Finished	1 3/8	5.05		60.60
Carbon Steel	AISI 1018	Cold Finished	1 7/16	5.52		66.24
Carbon Steel	AISI 1018	Cold Finished	1 1/2	6.01		72.12
Carbon Steel	AISI 1018	Cold Finished	1 9/16	6.52		78.24
Carbon Steel	AISI 1018	Cold Finished	1 5/8	7.05		84.60
Carbon Steel	AISI 1018	Cold Finished	1 11/16	7.60		91.20
Carbon Steel	AISI 1018	Cold Finished	1 3/4	8.18		98.16
Carbon Steel	AISI 1018	Cold Finished	1 13/16	8.77		105.24
Carbon Steel	AISI 1018	Cold Finished	1 7/8	9.39		112.68
Carbon Steel	AISI 1018	Cold Finished	1 15/16	10.02		120.24
Carbon Steel	AISI 1018	Cold Finished	2	10.68		128.16
Carbon Steel	AISI 1018	Cold Finished	2 1/16	11.36		136.32
Carbon Steel	AISI 1018	Cold Finished	2 1/8	12.06		144.72
Carbon Steel	AISI 1018	Cold Finished	2 3/16	12.78		153.36
Carbon Steel	AISI 1018	Cold Finished	2 1/4	13.52		162.24
Carbon Steel	AISI 1018	Cold Finished	2 5/16	14.28		171.36
Carbon Steel	AISI 1018	Cold Finished	2 3/8	15.06	301.2	
Carbon Steel	AISI 1018	Cold Finished	2 7/16	15.87	317.4	
Carbon Steel	AISI 1018	Cold Finished	2 1/2	16.69	333.8	

Carbon Steel	AISI 1018	Cold Finished	2 9/16	17.53	350.6	
Carbon Steel	AISI 1018	Cold Finished	2 5/8	18.40	368.0	
Carbon Steel	AISI 1018	Cold Finished	2 11/16	19.29	385.8	
Carbon Steel	AISI 1018	Cold Finished	2 3/4	20.20	404.0	
Carbon Steel	AISI 1018	Cold Finished	2 13/16	21.12	422.4	
Carbon Steel	AISI 1018	Cold Finished	2 7/8	22.07	441.4	
Carbon Steel	AISI 1018	Cold Finished	2 15/16	23.04	460.8	
Carbon Steel	AISI 1018	Cold Finished	3	24.03	480.6	288.36
Carbon Steel	AISI 1018	Cold Finished	3 1/16	25.05	500.8	
Carbon Steel	AISI 1018	Cold Finished	3 1/8	26.08	521.6	
Carbon Steel	AISI 1018	Cold Finished	3 3/16	27.13	542.6	
Carbon Steel	AISI 1018	Cold Finished	3 1/4	28.21	564.2	
Carbon Steel	AISI 1018	Cold Finished	3 5/16	29.30	586.0	
Carbon Steel	AISI 1018	Cold Finished	3 3/8	30.42	608.4	
Carbon Steel	AISI 1018	Cold Finished	3 7/16	31.55	631.0	
Carbon Steel	AISI 1018	Cold Finished	3 1/2	32.71	654.2	
Carbon Steel	AISI 1018	Cold Finished	3 9/16	33.89	677.8	
Carbon Steel	AISI 1018	Cold Finished	3 5/8	35.09	701.8	
Carbon Steel	AISI 1018	Cold Finished	3 11/16	36.31	726.2	
Carbon Steel	AISI 1018	Cold Finished	3 3/4	37.55	751.0	
Carbon Steel	AISI 1018	Cold Finished	3 13/16	38.81	776.2	
Carbon Steel	AISI 1018	Cold Finished	3 7/8	40.10		802.6

Carbon Steel	AISI 1018	Cold Finished	3 15/16	41.40	828.0
Carbon Steel	AISI 1018	Cold Finished	4	42.73	854.6
Carbon Steel	AISI 1018	Cold Finished	4 1/8	45.44	908.8
Carbon Steel	AISI 1018	Cold Finished	4 3/16	46.83	936.6
Carbon Steel	AISI 1018	Cold Finished	4 1/4	48.23	964.6
Carbon Steel	AISI 1018	Cold Finished	4 5/16	49.66	993.2
Carbon Steel	AISI 1018	Cold Finished	4 3/8	51.11	1022.2
Carbon Steel	AISI 1018	Cold Finished	4 7/16	52.58	1051.6
Carbon Steel	AISI 1018	Cold Finished	4 1/2	54.07	1081.6
Carbon Steel	AISI 1018	Cold Finished	4 9/16	55.59	1111.8
Carbon Steel	AISI 1018	Cold Finished	4 5/8	57.12	1143.4
Carbon Steel	AISI 1018	Cold Finished	4 11/16	58.67	1173.6
Carbon Steel	AISI 1018	Cold Finished	4 3/4	60.25	1205.0
Carbon Steel	AISI 1018	Cold Finished	4 7/8	63.46	1270.4
Carbon Steel	AISI 1018	Cold Finished	4 15/16	65.10	1302.0
Carbon Steel	AISI 1018	Cold Finished	5	66.76	1335.2
Carbon Steel	AISI 1018	Cold Finished	5 1/16	68.44	1368.8
Carbon Steel	AISI 1018	Cold Finished	5 1/8	70.14	1402.8
Carbon Steel	AISI 1018	Cold Finished	5 3/16	71.86	1437.2
Carbon Steel	AISI 1018	Cold Finished	5 1/4	73.60	1472.0
Carbon Steel	AISI 1018	Cold Finished	5 3/8	77.15	1543.0
Carbon Steel	AISI 1018	Cold Finished	5 7/16	78.95	1579.0

Carbon Steel	AISI 1018	Cold Finished	5 1/2	80.78	1615.6	
Carbon Steel	AISI 1018	Cold Finished	5 5/8	84.49	1689.8	
Carbon Steel	AISI 1018	Cold Finished	5 3/4	88.29	176.00	
Carbon Steel	AISI 1018	Cold Finished	5 7/8	92.17	1843.4	
Carbon Steel	AISI 1018	Cold Finished	5 15/16	91.14	1882.8	
Carbon Steel	AISI 1018	Cold Finished	6	96.13	1922.6	
Carbon Steel	AISI 1018	Cold Finished	6 1/8	100.18	2003.6	
Carbon Steel	AISI 1018	Cold Finished	6 1/4	104.31	2086.2	
Carbon Steel	AISI 1018	Cold Finished	6 1/2	112.82	2256.4	
Carbon Steel	AISI 1018	Cold Finished	6 3/4	121.67	2435.6	
Carbon Steel	AISI 1018	Cold Finished	7	130.85	2617.0	
Carbon Steel	AISI 1018	Cold Finished	7 1/4	140.36	2807.2	
Carbon Steel	AISI 1018	Cold Finished	7 1/2	150.21	3004.2	
Carbon Steel	AISI 1018	Cold Finished	8 1/2	192.93	3858.6	
Carbon Steel	AISI 1018	Cold Finished	9	216.30	4326.0	
Carbon Steel	AISI 1018	Cold Finished	10	267.04	5340.0	
Carbon Steel	AISI 1018	Cold Finished	12	384.53	7690.6	
Carbon Steel	AISI 1117	Cold Finished	1/8	.042		.504
Carbon Steel	AISI 1117	Cold Finished	5/32	.065		.780
Carbon Steel	AISI 1117	Cold Finished	3/16	.094		1.128
Carbon Steel	AISI 1117	Cold Finished	7/32	.128		1.536
Carbon Steel	AISI 1117	Cold Finished	1/4	.167		2.004

Carbon Steel	AISI 1117	Cold Finished	9/32	.211	2.532
Carbon Steel	AISI 1117	Cold Finished	5/16	.261	3.132
Carbon Steel	AISI 1117	Cold Finished	11/32	.316	7.972
Carbon Steel	AISI 1117	Cold Finished	3/8	.376	4.512
Carbon Steel	AISI 1117	Cold Finished	13/32	.441	5.292
Carbon Steel	AISI 1117	Cold Finished	7/16	.511	6.132
Carbon Steel	AISI 1117	Cold Finished	15/32	.587	7.044
Carbon Steel	AISI 1117	Cold Finished	1/2	.668	8.016
Carbon Steel	AISI 1117	Cold Finished	17/32	.754	9.048
Carbon Steel	AISI 1117	Cold Finished	9/16	.845	10.14
Carbon Steel	AISI 1117	Cold Finished	19/32	.941	11.29
Carbon Steel	AISI 1117	Cold Finished	5/8	1.04	12.48
Carbon Steel	AISI 1117	Cold Finished	11/16	1.26	15.12
Carbon Steel	AISI 1117	Cold Finished	3/4	1.50	18.00
Carbon Steel	AISI 1117	Cold Finished	13/16	1.76	21.12
Carbon Steel	AISI 1117	Cold Finished	7/8	2.04	24.48
Carbon Steel	AISI 1117	Cold Finished	15/16	2.35	28.30
Carbon Steel	AISI 1117	Cold Finished	1	2.67	32.04
Carbon Steel	AISI 1117	Cold Finished	1 1/16	3.04	36.12
Carbon Steel	AISI 1117	Cold Finished	1 1/8	3.38	40.56
Carbon Steel	AISI 1117	Cold Finished	1 3/16	3.77	45.24
Carbon Steel	AISI 1117	Cold Finished	1 1/4	4.17	50.04

Carbon Steel	AISI 1117	Cold Finished	1 5/16	4.60	55.20
Carbon Steel	AISI 1117	Cold Finished	1 3/8	5.05	60.60
Carbon Steel	AISI 1117	Cold Finished	1 7/16	5.52	66.24
Carbon Steel	AISI 1117	Cold Finished	1 1/2	6.01	72.12
Carbon Steel	AISI 1117	Cold Finished	1 9/16	6.52	78.24
Carbon Steel	AISI 1117	Cold Finished	1 5/8	7.05	84.60
Carbon Steel	AISI 1117	Cold Finished	1 11/16	7.60	91.20
Carbon Steel	AISI 1117	Cold Finished	1 3/4	8.18	98.16
Carbon Steel	AISI 1117	Cold Finished	1 13/16	8.77	105.24
Carbon Steel	AISI 1117	Cold Finished	1 7/8	9.39	112.68
Carbon Steel	AISI 1117	Cold Finished	1 15/16	10.02	120.24
Carbon Steel	AISI 1117	Cold Finished	2	10.68	128.16
Carbon Steel	AISI 1117	Cold Finished	2 1/16	11.36	136.32
Carbon Steel	AISI 1117	Cold Finished	2 1/8	12.06	144.72
Carbon Steel	AISI 1117	Cold Finished	2 3/16	12.78	153.36
Carbon Steel	AISI 1117	Cold Finished	2 1/4	13.52	162.24
Carbon Steel	AISI 1117	Cold Finished	2 5/16	14.28	171.36
Carbon Steel	AISI 1117	Cold Finished	2 3/8	15.06	180.72
Carbon Steel	AISI 1117	Cold Finished	2 7/16	15.87	190.44
Carbon Steel	AISI 1117	Cold Finished	2 1/2	16.69	200.28
Carbon Steel	AISI 1117	Cold Finished	2 9/16	17.53	210.36
Carbon Steel	AISI 1117	Cold Finished	2 5/8	18.40	220.80

Carbon Steel	AISI 1117	Cold Finished	2 11/16	19.29	231.40
Carbon Steel	AISI 1117	Cold Finished	2 3/4	20.19	242.28
Carbon Steel	AISI 1117	Cold Finished	2 13/16	21.12	253.44
Carbon Steel	AISI 1117	Cold Finished	2 7/8	22.07	264.84
Carbon Steel	AISI 1117	Cold Finished	2 15/16	23.04	276.48
Carbon Steel	AISI 1117	Cold Finished	3	24.03	288.36
Carbon Steel	AISI 1117	Cold Finished	3 1/8	26.08	312.96
Carbon Steel	AISI 1117	Cold Finished	3 3/16	27.13	325.56
Carbon Steel	AISI 1117	Cold Finished	3 1/4	28.21	338.52
Carbon Steel	AISI 1117	Cold Finished	3 5/16	29.30	
Carbon Steel	AISI 1117	Cold Finished	3 3/8	30.42	365.04
Carbon Steel	AISI 1117	Cold Finished	3 7/16	31.55	
Carbon Steel	AISI 1117	Cold Finished	3 1/2	32.71	392.52
Carbon Steel	AISI 1117	Cold Finished	3 5/8	35.09	421.08
Carbon Steel	AISI 1117	Cold Finished	3 3/4	37.55	450.06
Carbon Steel	AISI 1117	Cold Finished	3 7/8	40.10	481.20
Carbon Steel	AISI 1117	Cold Finished	4	42.73	512.76
Carbon Steel	AISI 1117	Cold Finished	4 1/8	45.44	
Carbon Steel	AISI 1117	Cold Finished	4 3/16	46.83	
Carbon Steel	AISI 1117	Cold Finished	4 1/4	48.23	578.76
Carbon Steel	AISI 1117	Cold Finished	4 3/8	51.11	
Carbon Steel	AISI 1117	Cold Finished	4 1/2	54.08	648.96

Carbon Steel	AISI 1117	Cold Finished	4 5/8	57.12	
Carbon Steel	AISI 1117	Cold Finished	4 3/4	60.25	
Carbon Steel	AISI 1117	Cold Finished	4 7/8	63.46	
Carbon Steel	AISI 1117	Cold Finished	5	66.76	
Carbon Steel	AISI 1117	Cold Finished	5 1/4	73.60	
Carbon Steel	AISI 1117	Cold Finished	5 1/2	80.78	
Carbon Steel	AISI 1117	Cold Finished	5 3/4	88.29	
Carbon Steel	AISI 1117	Cold Finished	6	96.13	
Carbon Steel	AISI 1141	Cold Finished	5/32	.065	.780
Carbon Steel	AISI 1141	Cold Finished	3/16	.094	1.128
Carbon Steel	AISI 1141	Cold Finished	7/32	.128	1.536
Carbon Steel	AISI 1141	Cold Finished	1/4	.167	2.004
Carbon Steel	AISI 1141	Cold Finished	5/16	.261	3.132
Carbon Steel	AISI 1141	Cold Finished	3/8	.376	4.512
Carbon Steel	AISI 1141	Cold Finished	7/16	.511	6.132
Carbon Steel	AISI 1141	Cold Finished	1/2	.668	8.016
Carbon Steel	AISI 1141	Cold Finished	9/16	.845	10.14
Carbon Steel	AISI 1141	Cold Finished	5/8	1.04	12.48
Carbon Steel	AISI 1141	Cold Finished	11/16	1.26	15.12
Carbon Steel	AISI 1141	Cold Finished	3/4	1.50	18.00
Carbon Steel	AISI 1141	Cold Finished	13/16	1.76	21.12
Carbon Steel	AISI 1141	Cold Finished	7/8	2.04	24.48

Carbon Steel	AISI 1141	Cold Finished	15/16	2.35	28.30
Carbon Steel	AISI 1141	Cold Finished	1	2.67	32.04
Carbon Steel	AISI 1141	Cold Finished	1 1/16	3.04	36.12
Carbon Steel	AISI 1141	Cold Finished	1 1/8	3.38	40.56
Carbon Steel	AISI 1141	Cold Finished	1 3/16	3.77	45.24
Carbon Steel	AISI 1141	Cold Finished	1 1/4	4.17	50.04
Carbon Steel	AISI 1141	Cold Finished	1 5/16	4.60	55.20
Carbon Steel	AISI 1141	Cold Finished	1 3/8	5.05	60.60
Carbon Steel	AISI 1141	Cold Finished	1 7/16	5.52	66.24
Carbon Steel	AISI 1141	Cold Finished	1 1/2	6.01	72.12
Carbon Steel	AISI 1141	Cold Finished	1 9/16	6.52	78.24
Carbon Steel	AISI 1141	Cold Finished	1 5/8	7.05	84.60
Carbon Steel	AISI 1141	Cold Finished	1 3/4	8.18	98.16
Carbon Steel	AISI 1141	Cold Finished	1 7/8	9.39	112.68
Carbon Steel	AISI 1141	Cold Finished	1 15/16	10.02	120.24
Carbon Steel	AISI 1141	Cold Finished	2	10.68	128.16
Carbon Steel	AISI 1141	Cold Finished	2 1/8	12.06	144.72
Carbon Steel	AISI 1141	Cold Finished	2 3/16	12.78	153.36
Carbon Steel	AISI 1141	Cold Finished	2 1/4	13.52	162.24
Carbon Steel	AISI 1141	Cold Finished	2 3/8	15.06	180.72
Carbon Steel	AISI 1141	Cold Finished	2 1/2	16.69	200.28
Carbon Steel	AISI 1141	Cold Finished	2 5/8	18.40	220.80

Carbon Steel	AISI 1141	Cold Finished	2 11/16	19.29	231.40
Carbon Steel	AISI 1141	Cold Finished	2 3/4	20.19	242.28
Carbon Steel	AISI 1141	Cold Finished	2 13/16	21.12	253.44
Carbon Steel	AISI 1141	Cold Finished	2 7/8	22.07	264.84
Carbon Steel	AISI 1141	Cold Finished	2 15/16	23.04	276.48
Carbon Steel	AISI 1141	Cold Finished	2 15/16	23.04	276.48
Carbon Steel	AISI 1141	Cold Finished	3	24.03	288.36
Carbon Steel	AISI 1141	Cold Finished	3 1/8	26.08	312.96
Carbon Steel	AISI 1141	Cold Finished	3 1/4	28.21	338.52
Carbon Steel	AISI 1141	Cold Finished	3 3/8	30.42	365.04
Carbon Steel	AISI 1141	Cold Finished	3 1/2	32.71	392.52
Carbon Steel	AISI 1141	Cold Finished	3 3/4	37.55	450.06
Carbon Steel	AISI 1141	Cold Finished	4	42.73	512.76
Carbon Steel	AISI 1144	Cold Finished	5/16	.261	3.132
Carbon Steel	AISI 1144	Cold Finished	3/8	.376	4.512
Carbon Steel	AISI 1144	Cold Finished	7/16	.511	6.132
Carbon Steel	AISI 1144	Cold Finished	1/2	.668	8.016
Carbon Steel	AISI 1144	Cold Finished	9/16	.845	10.14
Carbon Steel	AISI 1144	Cold Finished	5/8	1.04	12.48
Carbon Steel	AISI 1144	Cold Finished	11/16	1.26	15.12
Carbon Steel	AISI 1144	Cold Finished	3/4	1.50	18.00
Carbon Steel	AISI 1144	Cold Finished	13/16	1.76	21.12

Carbon Steel	AISI 1144	Cold Finished	7/8	2.04	24.48
Carbon Steel	AISI 1144	Cold Finished	15/16	2.35	28.30
Carbon Steel	AISI 1144	Cold Finished	1	2.67	32.04
Carbon Steel	AISI 1144	Cold Finished	1 1/16	3.04	36.12
Carbon Steel	AISI 1144	Cold Finished	1 1/8	3.38	40.56
Carbon Steel	AISI 1144	Cold Finished	1 1/4	4.17	50.04
Carbon Steel	AISI 1144	Cold Finished	1 3/8	5.05	60.60
Carbon Steel	AISI 1144	Cold Finished	1 1/2	6.01	72.12
Carbon Steel	AISI 1144	Cold Finished	1 5/8	7.05	84.60
Carbon Steel	AISI 1144	Cold Finished	1 3/4	8.18	98.16
Carbon Steel	AISI 1144	Cold Finished	1 7/8	9.39	112.68
Carbon Steel	AISI 1144	Cold Finished	2	10.68	128.16
Carbon Steel	AISI 1144	Cold Finished	2 1/4	13.52	162.24
Carbon Steel	AISI 1144	Cold Finished	2 3/8	15.06	180.72
Carbon Steel	AISI 1144	Cold Finished	2 1/2	16.69	200.28
Carbon Steel	AISI 1144	Cold Finished	2 5/8	18.40	220.80
Carbon Steel	AISI 1144	Cold Finished	3 1/8	26.08	312.96
Carbon Steel	AISI 1144	Cold Finished	3 1/2	32.71	392.52
Carbon Steel	AISI 1144	Cold Finished	3 3/4	37.55	450.06
Carbon Steel	AISI 1144	Cold Finished	4 3/4	60.25	
Carbon Steel	AISI 11L17	Cold Finished	3/16	.094	1.128
Carbon Steel	AISI 11L17	Cold Finished	7/32	.128	1.536

Carbon Steel	AISI 11L17	Cold Finished	1/4	.167	2.004
Carbon Steel	AISI 11L17	Cold Finished	9/32	.211	2.532
Carbon Steel	AISI 11L17	Cold Finished	19/64	.238	2.820
Carbon Steel	AISI 11L17	Cold Finished	5/16	.261	3.132
Carbon Steel	AISI 11L17	Cold Finished	11/32	.316	7.972
Carbon Steel	AISI 11L17	Cold Finished	3/8	.376	4.512
Carbon Steel	AISI 11L17	Cold Finished	13/32	.441	5.292
Carbon Steel	AISI 11L17	Cold Finished	7/16	.511	6.132
Carbon Steel	AISI 11L17	Cold Finished	15/32	.587	7.044
Carbon Steel	AISI 11L17	Cold Finished	1/2	.668	8.016
Carbon Steel	AISI 11L17	Cold Finished	17/32	.754	9.048
Carbon Steel	AISI 11L17	Cold Finished	9/16	.845	10.14
Carbon Steel	AISI 11L17	Cold Finished	19/32	.941	11.29
Carbon Steel	AISI 11L17	Cold Finished	5/8	1.04	12.48
Carbon Steel	AISI 11L17	Cold Finished	21/32	1.15	13.80
Carbon Steel	AISI 11L17	Cold Finished	11/16	1.26	15.12
Carbon Steel	AISI 11L17	Cold Finished	23/32	1.38	16.56
Carbon Steel	AISI 11L17	Cold Finished	3/4	1.50	18.00
Carbon Steel	AISI 11L17	Cold Finished	13/16	1.76	21.12
Carbon Steel	AISI 11L17	Cold Finished	7/8	2.04	24.48
Carbon Steel	AISI 11L17	Cold Finished	15/16	2.35	28.30
Carbon Steel	AISI 11L17	Cold Finished	1	2.67	32.04

Carbon Steel	AISI 11L17	Cold Finished	1 1/16	3.04	36.12
Carbon Steel	AISI 11L17	Cold Finished	1 1/8	3.38	40.56
Carbon Steel	AISI 11L17	Cold Finished	1 3/16	3.77	45.24
Carbon Steel	AISI 11L17	Cold Finished	1 1/4	4.17	50.04
Carbon Steel	AISI 11L17	Cold Finished	1 5/16	4.60	55.20
Carbon Steel	AISI 11L17	Cold Finished	1 3/8	5.05	60.60
Carbon Steel	AISI 11L17	Cold Finished	1 7/16	5.52	66.24
Carbon Steel	AISI 11L17	Cold Finished	1 1/2	6.01	72.12
Carbon Steel	AISI 11L17	Cold Finished	1 9/16	6.52	78.24
Carbon Steel	AISI 11L17	Cold Finished	1 5/8	7.05	84.60
Carbon Steel	AISI 11L17	Cold Finished	1 11/16	7.60	91.20
Carbon Steel	AISI 11L17	Cold Finished	1 3/4	8.18	98.16
Carbon Steel	AISI 11L17	Cold Finished	1 13/16	8.77	105.24
Carbon Steel	AISI 11L17	Cold Finished	1 7/8	9.39	112.68
Carbon Steel	AISI 11L17	Cold Finished	1 15/16	10.02	120.24
Carbon Steel	AISI 11L17	Cold Finished	2	10.68	128.16
Carbon Steel	AISI 11L17	Cold Finished	2 1/16	11.36	136.32
Carbon Steel	AISI 11L17	Cold Finished	2 1/8	12.06	144.72
Carbon Steel	AISI 11L17	Cold Finished	2 3/16	12.78	153.36
Carbon Steel	AISI 11L17	Cold Finished	2 1/4	13.52	162.24
Carbon Steel	AISI 11L17	Cold Finished	2 3/8	15.06	180.72
Carbon Steel	AISI 11L17	Cold Finished	2 7/16	15.87	190.44

Carbon Steel	AISI 11L17	Cold Finished	2 1/2	16.69	200.28
Carbon Steel	AISI 11L17	Cold Finished	2 5/8	18.40	220.80
Carbon Steel	AISI 11L17	Cold Finished	2 3/4	20.19	242.28
Carbon Steel	AISI 11L17	Cold Finished	2 7/8	22.07	264.84
Carbon Steel	AISI 11L17	Cold Finished	2 15/16	23.04	276.48
Carbon Steel	AISI 11L17	Cold Finished	3	24.03	288.36
Carbon Steel	AISI 11L17	Cold Finished	3 1/8	26.08	312.96
Carbon Steel	AISI 11L17	Cold Finished	3 1/4	28.21	338.52
Carbon Steel	AISI 11L17	Cold Finished	3 3/8	30.42	365.04
Carbon Steel	AISI 11L17	Cold Finished	3 1/2	32.71	392.52
Carbon Steel	AISI 11L17	Cold Finished	3 5/8	35.09	421.08
Carbon Steel	AISI 11L17	Cold Finished	3 3/4	37.55	450.06
Carbon Steel	AISI 11L17	Cold Finished	4	42.73	512.76
Carbon Steel	AISI 11L17	Cold Finished	4 1/8	45.44	
Carbon Steel	AISI 11L17	Cold Finished	4 1/4	48.23	578.76
Carbon Steel	AISI 11L17	Cold Finished	4 1/2	54.08	648.96
Carbon Steel	AISI 11L17	Cold Finished	4 5/8	57.12	
Carbon Steel	AISI 11L17	Cold Finished	4 3/4	60.25	
Carbon Steel	AISI 11L17	Cold Finished	5	66.76	
Carbon Steel	AISI 11L17	Cold Finished	5 1/4	73.60	
Carbon Steel	AISI 11L17	Cold Finished	5 1/2	80.78	
Carbon Steel	AISI 11L17	Cold Finished	5 5/8	84.49	

Carbon Steel	AISI 11L17	Cold Finished	6	96.13	
Carbon Steel	AISI 11L17	Cold Finished	6 1/2	112.82	
Carbon Steel	AISI 11L17	Cold Finished	7	130.85	
Carbon Steel	AISI 11L17	Cold Finished	7 1/2	150.21	
Carbon Steel	AISI 11L17	Cold Finished	8	170.90	
Carbon Steel	AISI 1215	Cold Finished	1/16	.010	.120
Carbon Steel	AISI 1215	Cold Finished	3/32	.023	.276
Carbon Steel	AISI 1215	Cold Finished	7/64	.032	.384
Carbon Steel	AISI 1215	Cold Finished	1/8	.042	.504
Carbon Steel	AISI 1215	Cold Finished	9/64	.053	.636
Carbon Steel	AISI 1215	Cold Finished	5/32	.065	.780
Carbon Steel	AISI 1215	Cold Finished	11/64	.079	.948
Carbon Steel	AISI 1215	Cold Finished	3/16	.094	1.128
Carbon Steel	AISI 1215	Cold Finished	13/64	.110	1.320
Carbon Steel	AISI 1215	Cold Finished	7/32	.128	1.536
Carbon Steel	AISI 1215	Cold Finished	15/64	.147	1.764
Carbon Steel	AISI 1215	Cold Finished	1/4	.167	2.004
Carbon Steel	AISI 1215	Cold Finished	17/64	.188	2.256
Carbon Steel	AISI 1215	Cold Finished	9/32	.211	2.532
Carbon Steel	AISI 1215	Cold Finished	19/64	.235	2.820
Carbon Steel	AISI 1215	Cold Finished	5/16	.261	3.132
Carbon Steel	AISI 1215	Cold Finished	21/64	.288	3.456

Carbon Steel	AISI 1215	Cold Finished	11/32	.316	3.792
Carbon Steel	AISI 1215	Cold Finished	23/64	.345	4.140
Carbon Steel	AISI 1215	Cold Finished	3/8	.376	4.512
Carbon Steel	AISI 1215	Cold Finished	25/64	.408	4.896
Carbon Steel	AISI 1215	Cold Finished	13/32	.441	5.292
Carbon Steel	AISI 1215	Cold Finished	27/64	.475	5.700
Carbon Steel	AISI 1215	Cold Finished	7/16	.511	6.132
Carbon Steel	AISI 1215	Cold Finished	29/64	.548	6.576
Carbon Steel	AISI 1215	Cold Finished	15/32	.587	7.044
Carbon Steel	AISI 1215	Cold Finished	1/2	.668	8.016
Carbon Steel	AISI 1215	Cold Finished	17/32	.754	9.048
Carbon Steel	AISI 1215	Cold Finished	9/16	.845	10.14
Carbon Steel	AISI 1215	Cold Finished	19/32	.941	11.29
Carbon Steel	AISI 1215	Cold Finished	5/8	1.043	12.48
Carbon Steel	AISI 1215	Cold Finished	21/32	1.150	13.80
Carbon Steel	AISI 1215	Cold Finished	11/16	1.262	15.12
Carbon Steel	AISI 1215	Cold Finished	23/32	1.380	16.56
Carbon Steel	AISI 1215	Cold Finished	3/4	1.502	18.00
Carbon Steel	AISI 1215	Cold Finished	25/32	1.631	19.57
Carbon Steel	AISI 1215	Cold Finished	13/16	1.763	21.12
Carbon Steel	AISI 1215	Cold Finished	27/32	1.901	22.81
Carbon Steel	AISI 1215	Cold Finished	7/8	2.045	24.48

Carbon Steel	AISI 1215	Cold Finished	29/32	2.193	26.32
Carbon Steel	AISI 1215	Cold Finished	15/16	2.347	28.20
Carbon Steel	AISI 1215	Cold Finished	31/32	2.506	30.07
Carbon Steel	AISI 1215	Cold Finished	1	2.670	32.04
Carbon Steel	AISI 1215	Cold Finished	1 1/32	2.840	34.08
Carbon Steel	AISI 1215	Cold Finished	1 1/16	3.015	36.12
Carbon Steel	AISI 1215	Cold Finished	1 1/8	3.380	40.56
Carbon Steel	AISI 1215	Cold Finished	1 3/16	3.766	45.24
Carbon Steel	AISI 1215	Cold Finished	1 1/4	4.172	50.04
Carbon Steel	AISI 1215	Cold Finished	1 5/16	4.600	55.20
Carbon Steel	AISI 1215	Cold Finished	1 3/8	5.049	60.60
Carbon Steel	AISI 1215	Cold Finished	1 7/16	5.518	66.24
Carbon Steel	AISI 1215	Cold Finished	1 1/2	6.008	72.12
Carbon Steel	AISI 1215	Cold Finished	1 9/16	6.519	78.24
Carbon Steel	AISI 1215	Cold Finished	1 5/8	7.051	84.60
Carbon Steel	AISI 1215	Cold Finished	1 11/16	7.604	91.20
Carbon Steel	AISI 1215	Cold Finished	1 3/4	8.178	98.16
Carbon Steel	AISI 1215	Cold Finished	1 13/16	8.773	105.24
Carbon Steel	AISI 1215	Cold Finished	1 7/8	9.388	112.68
Carbon Steel	AISI 1215	Cold Finished	1 15/16	10.02	120.24
Carbon Steel	AISI 1215	Cold Finished	2	10.68	128.16
Carbon Steel	AISI 1215	Cold Finished	2 1/16	11.36	136.32

Carbon Steel	AISI 1215	Cold Finished	2 1/8	12.06	144.72
Carbon Steel	AISI 1215	Cold Finished	2 3/16	12.78	153.36
Carbon Steel	AISI 1215	Cold Finished	2 1/4	13.52	162.24
Carbon Steel	AISI 1215	Cold Finished	2 5/16	14.28	171.36
Carbon Steel	AISI 1215	Cold Finished	2 3/8	15.06	180.72
Carbon Steel	AISI 1215	Cold Finished	2 7/16	15.87	190.44
Carbon Steel	AISI 1215	Cold Finished	2 1/2	16.69	200.28
Carbon Steel	AISI 1215	Cold Finished	2 5/8	18.40	220.80
Carbon Steel	AISI 1215	Cold Finished	2 11/16	19.29	231.40
Carbon Steel	AISI 1215	Cold Finished	2 3/4	20.19	242.28
Carbon Steel	AISI 1215	Cold Finished	2 13/16	21.12	253.44
Carbon Steel	AISI 1215	Cold Finished	2 7/8	22.07	264.84
Carbon Steel	AISI 1215	Cold Finished	2 15/16	23.04	276.48
Carbon Steel	AISI 1215	Cold Finished	3	24.03	288.36
Carbon Steel	AISI 1215	Cold Finished	3 1/8	26.08	312.96
Carbon Steel	AISI 1215	Cold Finished	3 1/4	28.21	338.52
Carbon Steel	AISI 1215	Cold Finished	3 3/8	30.42	365.04
Carbon Steel	AISI 1215	Cold Finished	3 1/2	32.71	392.52
Carbon Steel	AISI 1215	Cold Finished	3 5/8	35.09	421.08
Carbon Steel	AISI 1215	Cold Finished	3 3/4	37.55	450.60
Carbon Steel	AISI 1215	Cold Finished	3 7/8	40.10	481.20
Carbon Steel	AISI 1215	Cold Finished	4	42.73	512.76

Carbon Steel	AISI 1215	Cold Finished	4 1/4	48.23	578.76
Carbon Steel	AISI 1215	Cold Finished	4 3/8	51.11	613.32
Carbon Steel	AISI 1215	Cold Finished	4 1/2	54.08	648.96
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1/8	.042	.504
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	5/32	.065	.780
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	3/16	.094	1.128
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	7/32	.128	1.536
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1/4	.167	2.004
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	9/32	.211	2.532
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	5/16	.261	3.132
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	11/32	.316	3.792
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	3/8	.376	4.512
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	13/32	.441	5.292
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	7/16	.511	6.132
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	15/32	.587	7.044
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1/2	.668	8.016
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	17/32	.754	9.048
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	9/16	.845	10.14
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	19/32	.941	11.29
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	5/8	1.043	12.48
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	11/16	1.262	15.12
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	3/4	1.502	18.00

Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	13/16	1.763	21.12
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	7/8	2.045	24.48
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	15/16	2.347	28.20
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1	2.670	32.04
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 1/16	3.015	36.12
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 1/8	3.380	40.56
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 3/16	3.766	45.25
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 1/4	4.172	50.04
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 5/16	4.600	55.20
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 3/8	5.049	60.60
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 7/16	5.518	66.24
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 1/2	6.008	72.12
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 9/16	6.519	78.24
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 5/8	7.051	84.60
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 11/16	7.604	91.20
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 3/4	8.178	98.16
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 13/16	8.773	105.24
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 7/8	9.388	112.68
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	1 15/16	10.02	120.24
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	2	10.68	128.16
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	2 1/16	11.36	136.32
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	2 1/8	12.06	144.72

Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	2 3/16	12.78	153.36
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	2 1/4	13.52	162.24
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	2 5/16	14.28	171.36
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	2 3/8	15.06	180.72
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	2 1/2	16.69	200.28
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	2 5/8	18.40	220.80
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	2 11/16	19.29	231.40
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	2 3/4	20.19	242.28
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	2 13/16	21.12	253.44
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	2 7/8	22.07	264.84
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	3	24.03	288.36
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	3 1/8	26.08	312.96
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	3 1/4	28.21	338.52
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	3 3/8	30.42	365.04
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	3 1/2	32.71	392.52
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	3 5/8	35.09	421.08
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	3 3/4	37.55	450.60
Carbon Steel	AISI 12L14 (Ledloy A)	Cold Finished	3 7/8	40.10	481.20
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	1/4	.167	2.004
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	5/16	.261	3.132
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	3/8	.376	4.512
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	7/16	.511	6.132

Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	1/2	.668	8.016
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	9/16	.845	10.14
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	5/8	1.043	12.48
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	3/4	1.502	18.00
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	13/16	1.763	21.12
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	7/8	2.045	24.48
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	15/16	2.347	28.20
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	1	2.670	32.04
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	1 1/8	3.380	40.56
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	1 1/4	4.172	50.04
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	1 3/8	5.049	60.60
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	1 1/2	6.008	72.12
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	1 5/8	7.051	84.60
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	1 3/4	8.178	98.16
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	1 7/8	9.388	112.68
Carbon Steel	AISI 12L14-AX (Ledloy AX)	Cold Finished	2	10.68	128.16
Carbon Steel	Fatigue Proof	Cold Finished	3/8	.376	4.512
Carbon Steel	Fatigue Proof	Cold Finished	1/2	.668	8.016
Carbon Steel	Fatigue Proof	Cold Finished	5/8	1.04	12.48
Carbon Steel	Fatigue Proof	Cold Finished	3/4	1.50	18.00
Carbon Steel	Fatigue Proof	Cold Finished	7/8	2.04	24.48
Carbon Steel	Fatigue Proof	Cold Finished	15/16	2.35	28.20

Carbon Steel	Fatigue Proof	Cold Finished	1	2.67	32.04
Carbon Steel	Fatigue Proof	Cold Finished	1 1/16	3.01	36.12
Carbon Steel	Fatigue Proof	Cold Finished	1 1/8	3.38	40.56
Carbon Steel	Fatigue Proof	Cold Finished	1 3/16	3.77	45.24
Carbon Steel	Fatigue Proof	Cold Finished	1 1/4	4.17	50.04
Carbon Steel	Fatigue Proof	Cold Finished	1 3/8	5.05	60.60
Carbon Steel	Fatigue Proof	Cold Finished	1 1/2	6.01	72.12
Carbon Steel	Fatigue Proof	Cold Finished	1 5/8	7.05	84.60
Carbon Steel	Fatigue Proof	Cold Finished	1 3/4	8.18	98.16
Carbon Steel	Stress Proof	Cold Finished	3/8	.376	4.512
Carbon Steel	Stress Proof	Cold Finished	7/16	.511	6.132
Carbon Steel	Stress Proof	Cold Finished	1/2	.668	8.016
Carbon Steel	Stress Proof	Cold Finished	9/16	.845	10.14
Carbon Steel	Stress Proof	Cold Finished	5/8	1.04	12.48
Carbon Steel	Stress Proof	Cold Finished	3/4	1.50	18.00
Carbon Steel	Stress Proof	Cold Finished	7/8	2.04	24.48
Carbon Steel	Stress Proof	Cold Finished	15/16	2.35	28.20
Carbon Steel	Stress Proof	Cold Finished	1	2.67	32.04
Carbon Steel	Stress Proof	Cold Finished	1 1/16	3.01	36.12
Carbon Steel	Stress Proof	Cold Finished	1 1/8	3.38	40.56
Carbon Steel	Stress Proof	Cold Finished	1 3/16	3.77	45.24
Carbon Steel	Stress Proof	Cold Finished	1 1/4	4.17	50.04

Carbon Steel	Stress Proof	Cold Finished	1 3/8	5.05	60.60
Carbon Steel	Stress Proof	Cold Finished	1 7/16	5.52	66.24
Carbon Steel	Stress Proof	Cold Finished	1 1/2	6.01	72.12
Carbon Steel	Stress Proof	Cold Finished	1 5/8	7.05	84.60
Carbon Steel	Stress Proof	Cold Finished	1 11/16	7.61	91.32
Carbon Steel	Stress Proof	Cold Finished	1 3/4	8.18	98.16
Carbon Steel	Stress Proof	Cold Finished	1 7/8	9.39	112.68
Carbon Steel	Stress Proof	Cold Finished	1 15/16	10.02	120.24
Carbon Steel	Stress Proof	Cold Finished	2	10.68	128.16
Carbon Steel	Stress Proof	Cold Finished	2 1/8	12.06	144.72
Carbon Steel	Stress Proof	Cold Finished	2 1/4	13.52	162.24
Carbon Steel	Stress Proof	Cold Finished	2 3/8	15.06	180.72
Carbon Steel	Stress Proof	Cold Finished	2 7/16	15.87	190.44
Carbon Steel	Stress Proof	Cold Finished	2 1/2	16.69	200.28
Carbon Steel	Stress Proof	Cold Finished	2 5/8	18.40	220.80
Carbon Steel	Stress Proof	Cold Finished	2 3/4	20.19	242.28
Carbon Steel	Stress Proof	Cold Finished	2 7/8	22.07	264.84
Carbon Steel	Stress Proof	Cold Finished	2 15/16	23.04	276.48
Carbon Steel	Stress Proof	Cold Finished	3	24.03	288.36
Carbon Steel	Stress Proof	Cold Finished	3 1/8	26.08	312.96
Carbon Steel	Stress Proof	Cold Finished	3 1/4	28.21	338.52
Stainless Steel	Type 303, Annealed and Centerless Ground		1/4	.167	

Stainless Steel	Type 303, Annealed and Centerless Ground	5/16	.261
Stainless Steel	Type 303, Annealed and Centerless Ground	3/8	.376
Stainless Steel	Type 303, Annealed and Centerless Ground	7/16	.511
Stainless Steel	Type 303, Annealed and Centerless Ground	1/2	.668
Stainless Steel	Type 303, Annealed and Centerless Ground	17/32	.754
Stainless Steel	Type 303, Annealed and Centerless Ground	9/16	.845
Stainless Steel	Type 303, Annealed and Centerless Ground	19/32	.942
Stainless Steel	Type 303, Annealed and Centerless Ground	5/8	1.04
Stainless Steel	Type 303, Annealed and Centerless Ground	21/32	1.15
Stainless Steel	Type 303, Annealed and Centerless Ground	11/16	1.26
Stainless Steel	Type 303, Annealed and Centerless Ground	3/4	1.50
Stainless Steel	Type 303, Annealed and Centerless Ground	13/16	1.76
Stainless Steel	Type 303, Annealed and Centerless Ground	7/8	2.04
Stainless Steel	Type 303, Annealed and Centerless Ground	29/32	2.19
Stainless Steel	Type 303, Annealed and Centerless Ground	15/16	2.35
Stainless Steel	Type 303, Annealed and Centerless Ground	1	2.67
Stainless Steel	Type 303, Annealed and Centerless Ground	1 1/16	3.01
Stainless Steel	Type 303, Annealed and Centerless Ground	1 1/8	3.38
Stainless Steel	Type 303, Annealed and Centerless Ground	1 3/16	3.77
Stainless Steel	Type 303, Annealed and Centerless Ground	1 1/4	4.17
Stainless Steel	Type 303, Annealed and Centerless Ground	1 5/16	4.60
Stainless Steel	Type 303, Annealed and Centerless Ground	1 3/8	5.05

Stainless Steel	Type 303, Annealed and Centerless Ground	1 7/16	5.52
Stainless Steel	Type 303, Annealed and Centerless Ground	1 1/2	6.01
Stainless Steel	Type 303, Annealed and Centerless Ground	1 9/16	6.52
Stainless Steel	Type 303, Annealed and Centerless Ground	1 5/8	7.05
Stainless Steel	Type 303, Annealed and Centerless Ground	1 11/16	7.60
Stainless Steel	Type 303, Annealed and Centerless Ground	1 3/4	8.18
Stainless Steel	Type 303, Annealed and Centerless Ground	1 13/16	8.77
Stainless Steel	Type 303, Annealed and Centerless Ground	1 7/8	9.39
Stainless Steel	Type 303, Annealed and Centerless Ground	1 15/16	10.02
Stainless Steel	Type 303, Annealed and Centerless Ground	2	10.68
Stainless Steel	Type 303, Annealed and Centerless Ground	2 1/16	11.36
Stainless Steel	Type 303, Annealed and Centerless Ground	2 1/8	12.06
Stainless Steel	Type 303, Annealed and Centerless Ground	2 3/16	12.78
Stainless Steel	Type 303, Annealed and Centerless Ground	2 1/4	13.52
Stainless Steel	Type 303, Annealed and Centerless Ground	2 5/16	14.28
Stainless Steel	Type 303, Annealed and Centerless Ground	2 3/8	15.06
Stainless Steel	Type 303, Annealed and Centerless Ground	2 7/16	15.87
Stainless Steel	Type 303, Annealed and Centerless Ground	2 1/2	16.69
Stainless Steel	Type 303, Annealed and Centerless Ground	2 9/16	17.53
Stainless Steel	Type 303, Annealed and Centerless Ground	2 5/8	18.40
Stainless Steel	Type 303, Annealed and Centerless Ground	2 11/16	19.29
Stainless Steel	Type 303, Annealed and Centerless Ground	2 3/4	20.20

Stainless Steel	Type 303, Annealed and Centerless Ground	2 13/16	21.12
Stainless Steel	Type 303, Annealed and Centerless Ground	2 7/8	22.07
Stainless Steel	Type 303, Annealed and Centerless Ground	2 15/16	23.04
Stainless Steel	Type 303, Annealed and Centerless Ground	3	24.03
Stainless Steel	Type 303, Annealed and Centerless Ground	3 1/8	26.08
Stainless Steel	Type 303, Annealed and Centerless Ground	3 1/4	28.21
Stainless Steel	Type 303, Annealed and Centerless Ground	3 3/8	30.42
Stainless Steel	Type 303, Annealed and Centerless Ground	3 1/2	32.71
Stainless Steel	Type 303, Annealed and Centerless Ground	3 3/4	37.55
Stainless Steel	Type 303, Annealed and Centerless Ground	4	42.73
Stainless Steel	Type 303, Annealed and Centerless Ground	4 1/4	48.23
Stainless Steel	Type 303, Annealed and Centerless Ground	4 1/2	54.08
Stainless Steel	Type 303, Annealed and Centerless Ground	4 3/4	60.25
Stainless Steel	Type 303, Annealed and Centerless Ground	5	66.76
Stainless Steel	Type 303, Annealed and Centerless Ground	5 1/4	73.60
Stainless Steel	Type 303, Annealed and Centerless Ground	5 1/2	80.78
Stainless Steel	Type 303, Annealed and Centerless Ground	6	96.13
Stainless Steel	Type 303, Annealed and Cold Drawn	1/16	.010
Stainless Steel	Type 303, Annealed and Cold Drawn	3/32	.024
Stainless Steel	Type 303, Annealed and Cold Drawn	1/8	.042
Stainless Steel	Type 303, Annealed and Cold Drawn	5/32	.065
Stainless Steel	Type 303, Annealed and Cold Drawn	3/16	.094

Stainless Steel	Type 303, Annealed and Cold Drawn	7/32	.128
Stainless Steel	Type 303, Annealed and Cold Drawn	1/4	.167
Stainless Steel	Type 303, Annealed and Cold Drawn	9/32	.211
Stainless Steel	Type 303, Annealed and Cold Drawn	5/16	.261
Stainless Steel	Type 303, Annealed and Cold Drawn	11/32	.316
Stainless Steel	Type 303, Annealed and Cold Drawn	3/8	.376
Stainless Steel	Type 303, Annealed and Cold Drawn	13/32	.441
Stainless Steel	Type 303, Annealed and Cold Drawn	7/16	.511
Stainless Steel	Type 303, Annealed and Cold Drawn	15/32	.587
Stainless Steel	Type 303, Annealed and Cold Drawn	1/2	.668
Stainless Steel	Type 303, Pump Shaft Quality, Centerless Groun	1/8	.042
Stainless Steel	Type 303, Pump Shaft Quality, Centerless Groun	3/16	.094
Stainless Steel	Type 303, Pump Shaft Quality, Centerless Groun	1/4	.167
Stainless Steel	Type 303, Pump Shaft Quality, Centerless Groun	5/16	.261
Stainless Steel	Type 303, Pump Shaft Quality, Centerless Groun	3/8	.376
Stainless Steel	Type 303, Pump Shaft Quality, Centerless Groun	1/2	.668
Stainless Steel	Type 303, Pump Shaft Quality, Centerless Groun	5/8	1.04
Stainless Steel	Type 303, Pump Shaft Quality, Centerless Groun	3/4	1.50
Stainless Steel	Type 303, Pump Shaft Quality, Centerless Groun	7/8	2.04
Stainless Steel	Type 304, Annealed and Centerless Ground	9/16	.845
Stainless Steel	Type 304, Annealed and Centerless Ground	5/8	1.04
Stainless Steel	Type 304, Annealed and Centerless Ground	11/16	1.26

Stainless Steel	Type 304, Annealed and Centerless Ground	3/4	1.50
Stainless Steel	Type 304, Annealed and Centerless Ground	13/16	1.76
Stainless Steel	Type 304, Annealed and Centerless Ground	7/8	2.04
Stainless Steel	Type 304, Annealed and Centerless Ground	15/16	2.35
Stainless Steel	Type 304, Annealed and Centerless Ground	1	2.67
Stainless Steel	Type 304, Annealed and Centerless Ground	1 1/16	3.01
Stainless Steel	Type 304, Annealed and Centerless Ground	1 1/8	3.38
Stainless Steel	Type 304, Annealed and Centerless Ground	1 3/16	3.77
Stainless Steel	Type 304, Annealed and Centerless Ground	1 1/4	4.17
Stainless Steel	Type 304, Annealed and Centerless Ground	1 5/16	4.60
Stainless Steel	Type 304, Annealed and Centerless Ground	1 3/8	5.05
Stainless Steel	Type 304, Annealed and Centerless Ground	1 7/16	5.52
Stainless Steel	Type 304, Annealed and Centerless Ground	1 1/2	6.01
Stainless Steel	Type 304, Annealed and Centerless Ground	1 9/16	6.52
Stainless Steel	Type 304, Annealed and Centerless Ground	1 5/8	7.05
Stainless Steel	Type 304, Annealed and Centerless Ground	1 11/16	7.60
Stainless Steel	Type 304, Annealed and Centerless Ground	1 3/4	8.18
Stainless Steel	Type 304, Annealed and Centerless Ground	1 13/16	8.77
Stainless Steel	Type 304, Annealed and Centerless Ground	1 7/8	9.39
Stainless Steel	Type 304, Annealed and Centerless Ground	1 15/16	10.02
Stainless Steel	Type 304, Annealed and Centerless Ground	2	10.68
Stainless Steel	Type 304, Annealed and Centerless Ground	2 1/8	12.06

Stainless Steel	Type 304, Annealed and Centerless Ground	2 1/4	13.52
Stainless Steel	Type 304, Annealed and Centerless Ground	2 3/8	15.06
Stainless Steel	Type 304, Annealed and Centerless Ground	2 1/2	16.69
Stainless Steel	Type 304, Annealed and Centerless Ground	2 9/16	17.53
Stainless Steel	Type 304, Annealed and Centerless Ground	2 5/8	18.40
Stainless Steel	Type 304, Annealed and Centerless Ground	2 7/8	22.07
Stainless Steel	Type 304, Annealed and Centerless Ground	3	24.03
Stainless Steel	Type 304, Annealed and Centerless Ground	3 1/4	28.21
Stainless Steel	Type 304, Annealed and Centerless Ground	3 1/2	32.71
Stainless Steel	Type 304, Annealed and Centerless Ground	3 3/4	37.55
Stainless Steel	Type 304, Annealed and Centerless Ground	4	42.73
Stainless Steel	Type 304, Annealed and Centerless Ground	4 1/4	48.23
Stainless Steel	Type 304, Annealed and Centerless Ground	4 1/2	54.08
Stainless Steel	Type 304, Annealed and Centerless Ground	4 3/4	60.25
Stainless Steel	Type 304, Annealed and Centerless Ground	5	66.76
Stainless Steel	Type 304, Annealed and Centerless Ground	5 1/2	80.78
Stainless Steel	Type 304, Annealed and Centerless Ground	6	96.13
Stainless Steel	Type 304, Annealed and Cold Drawn	1/16	.010
Stainless Steel	Type 304, Annealed and Cold Drawn	3/32	.024
Stainless Steel	Type 304, Annealed and Cold Drawn	1/8	.042
Stainless Steel	Type 304, Annealed and Cold Drawn	3/16	.094
Stainless Steel	Type 304, Annealed and Cold Drawn	1/4	.167

Stainless Steel	Type 304, Annealed and Cold Drawn		5/16	.261
Stainless Steel	Type 304, Annealed and Cold Drawn		3/8	.376
Stainless Steel	Type 304, Annealed and Cold Drawn		7/16	.511
Stainless Steel	Type 304, Annealed and Cold Drawn		1/2	.668
Stainless Steel	Type 309, Annealed and Pickled	Hot Rolled	1/4	.167
Stainless Steel	Type 309, Annealed and Pickled	Hot Rolled	3/8	.376
Stainless Steel	Type 309, Annealed and Pickled	Hot Rolled	1/2	.668
Stainless Steel	Type 309, Annealed and Pickled	Hot Rolled	5/8	1.04
Stainless Steel	Type 309, Annealed and Pickled	Hot Rolled	3/4	1.50
Stainless Steel	Type 309, Annealed and Pickled	Hot Rolled	7/8	2.04
Stainless Steel	Type 309, Annealed and Pickled	Hot Rolled	1	2.67
Stainless Steel	Type 309, Annealed and Pickled	Hot Rolled	1 1/4	4.17
Stainless Steel	Type 309, Annealed and Pickled	Hot Rolled	1 1/2	6.01
Stainless Steel	Type 309, Annealed and Pickled	Hot Rolled	1 3/4	8.18
Stainless Steel	Type 309, Annealed and Pickled	Hot Rolled	2	10.68
Stainless Steel	Type 316, Annealed and Centerless Ground		9/16	.845
Stainless Steel	Type 316, Annealed and Centerless Ground		5/8	1.04
Stainless Steel	Type 316, Annealed and Centerless Ground		11/16	1.26
Stainless Steel	Type 316, Annealed and Centerless Ground		3/4	1.50
Stainless Steel	Type 316, Annealed and Centerless Ground		13/16	1.76
Stainless Steel	Type 316, Annealed and Centerless Ground		7/8	2.04
Stainless Steel	Type 316, Annealed and Centerless Ground		15/16	2.35

Stainless Steel	Type 316, Annealed and Centerless Ground	1	2.67
Stainless Steel	Type 316, Annealed and Centerless Ground	1 1/8	3.38
Stainless Steel	Type 316, Annealed and Centerless Ground	1 3/16	3.77
Stainless Steel	Type 316, Annealed and Centerless Ground	1 1/4	4.17
Stainless Steel	Type 316, Annealed and Centerless Ground	1 3/8	5.05
Stainless Steel	Type 316, Annealed and Centerless Ground	1 7/16	5.52
Stainless Steel	Type 316, Annealed and Centerless Ground	1 1/2	6.01
Stainless Steel	Type 316, Annealed and Centerless Ground	1 5/8	7.05
Stainless Steel	Type 316, Annealed and Centerless Ground	1 3/4	8.18
Stainless Steel	Type 316, Annealed and Centerless Ground	1 7/8	9.39
Stainless Steel	Type 316, Annealed and Centerless Ground	1 15/16	10.02
Stainless Steel	Type 316, Annealed and Centerless Ground	2	10.68
Stainless Steel	Type 316, Annealed and Centerless Ground	2 1/8	12.06
Stainless Steel	Type 316, Annealed and Centerless Ground	2 1/4	13.52
Stainless Steel	Type 316, Annealed and Centerless Ground	2 3/8	15.06
Stainless Steel	Type 316, Annealed and Centerless Ground	2 7/16	15.87
Stainless Steel	Type 316, Annealed and Centerless Ground	2 1/2	16.69
Stainless Steel	Type 316, Annealed and Centerless Ground	2 9/16	17.53
Stainless Steel	Type 316, Annealed and Centerless Ground	2 5/8	18.40
Stainless Steel	Type 316, Annealed and Centerless Ground	2 7/8	22.07
Stainless Steel	Type 316, Annealed and Centerless Ground	3	24.03
Stainless Steel	Type 316, Annealed and Centerless Ground	3 1/4	28.21

Stainless Steel	Type 316, Annealed and Centerless Ground		3 1/2	32.71
Stainless Steel	Type 316, Annealed and Centerless Ground		3 3/4	37.55
Stainless Steel	Type 316, Annealed and Centerless Ground		4	42.73
Stainless Steel	Type 316, Annealed and Centerless Ground		4 1/2	54.08
Stainless Steel	Type 316, Annealed and Centerless Ground		5	66.76
Stainless Steel	Type 316, Annealed and Centerless Ground		5 1/2	80.78
Stainless Steel	Type 316, Annealed and Cold Drawn		1/8	.042
Stainless Steel	Type 316, Annealed and Cold Drawn		3/16	.094
Stainless Steel	Type 316, Annealed and Cold Drawn		1/4	.167
Stainless Steel	Type 316, Annealed and Cold Drawn		5/16	.261
Stainless Steel	Type 316, Annealed and Cold Drawn		3/8	.376
Stainless Steel	Type 316, Annealed and Cold Drawn		7/16	.511
Stainless Steel	Type 316, Annealed and Cold Drawn		1/2	.668
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	9/16	.845
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	5/8	1.04
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	3/4	1.50
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	13/16	1.76
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	1	2.67
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	1 1/4	4.17
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	1 3/8	5.05
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	1 1/2	6.01
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	1 3/4	8.18

Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	1 7/8	9.39
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	2	10.68
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	2 1/4	13.52
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	2 1/2	16.69
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	2 3/4	20.20
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	3	24.03
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	3 1/2	32.71
Stainless Steel	Type 321, Annealed and Centerless Ground	Hot Rolled	4	42.73
Stainless Steel	Type 321, Annealed and Cold Drawn	Hot Rolled	1/4	.167
Stainless Steel	Type 321, Annealed and Cold Drawn	Hot Rolled	5/16	.261
Stainless Steel	Type 321, Annealed and Cold Drawn	Hot Rolled	3/8	.376
Stainless Steel	Type 321, Annealed and Cold Drawn	Hot Rolled	7/16	.511
Stainless Steel	Type 321, Annealed and Cold Drawn	Hot Rolled	1/2	.668
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	3/8	.376
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	1/2	.668
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	5/8	1.04
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	3/4	1.50
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	1	2.67
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	1 1/4	4.17
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	1 1/2	6.01
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	1 3/4	8.18
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	2	10.68

Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	2 1/8	12.06
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	2 1/4	13.52
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	2 1/2	16.69
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	2 3/4	20.20
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	3	24.03
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	3 1/4	28.21
Stainless Steel	Type 330, Annealed--RA330 Chemistry	Hot Rolled	3 1/2	32.71
Stainless Steel	Type 347, Annealed and Centerless Ground	Hot Rolled	5/8	1.04
Stainless Steel	Type 347, Annealed and Centerless Ground	Hot Rolled	3/4	1.50
Stainless Steel	Type 347, Annealed and Centerless Ground	Hot Rolled	7/8	2.04
Stainless Steel	Type 347, Annealed and Centerless Ground	Hot Rolled	1	2.67
Stainless Steel	Type 347, Annealed and Centerless Ground	Hot Rolled	1 1/8	3.38
Stainless Steel	Type 347, Annealed and Centerless Ground	Hot Rolled	1 1/4	4.17
Stainless Steel	Type 347, Annealed and Centerless Ground	Hot Rolled	1 3/8	5.05
Stainless Steel	Type 347, Annealed and Centerless Ground	Hot Rolled	1 1/2	6.01
Stainless Steel	Type 347, Annealed and Centerless Ground	Hot Rolled	1 3/4	8.18
Stainless Steel	Type 347, Annealed and Centerless Ground	Hot Rolled	2 1/2	16.69
Stainless Steel	Type 347, Annealed and Centerless Ground	Hot Rolled	3	24.03
Stainless Steel	Type 347, Annealed and Centerless Ground	Hot Rolled	3 1/2	32.71
Stainless Steel	Type 347, Annealed and Centerless Ground	Hot Rolled	4	42.73
Stainless Steel	Type 347, Annealed and Cold Drawn	Hot Rolled	1/4	.167
Stainless Steel	Type 347, Annealed and Cold Drawn	Hot Rolled	3/8	.376

Stainless Steel	Type 347, Annealed and Cold Drawn	Hot Rolled	1/2	.668
Stainless Steel	Type 416, Annealed and Centerless Ground		1/4	.167
Stainless Steel	Type 416, Annealed and Centerless Ground		5/16	.261
Stainless Steel	Type 416, Annealed and Centerless Ground		3/8	.376
Stainless Steel	Type 416, Annealed and Centerless Ground		7/16	.511
Stainless Steel	Type 416, Annealed and Centerless Ground		1/2	.668
Stainless Steel	Type 416, Annealed and Centerless Ground		17/32	.754
Stainless Steel	Type 416, Annealed and Centerless Ground		9/16	.845
Stainless Steel	Type 416, Annealed and Centerless Ground		19/32	.942
Stainless Steel	Type 416, Annealed and Centerless Ground		5/8	1.04
Stainless Steel	Type 416, Annealed and Centerless Ground		21/32	1.15
Stainless Steel	Type 416, Annealed and Centerless Ground		11/16	1.26
Stainless Steel	Type 416, Annealed and Centerless Ground		3/4	1.50
Stainless Steel	Type 416, Annealed and Centerless Ground		13/16	1.76
Stainless Steel	Type 416, Annealed and Centerless Ground		7/8	2.04
Stainless Steel	Type 416, Annealed and Centerless Ground		15/16	2.35
Stainless Steel	Type 416, Annealed and Centerless Ground		1	2.67
Stainless Steel	Type 416, Annealed and Centerless Ground		1 1/16	3.01
Stainless Steel	Type 416, Annealed and Centerless Ground		1 1/8	3.38
Stainless Steel	Type 416, Annealed and Centerless Ground		1 3/16	3.77
Stainless Steel	Type 416, Annealed and Centerless Ground		1 1/4	4.17
Stainless Steel	Type 416, Annealed and Centerless Ground		1 5/16	4.60

Stainless Steel	Type 416, Annealed and Centerless Ground	1 3/8	5.05
Stainless Steel	Type 416, Annealed and Centerless Ground	1 7/16	5.52
Stainless Steel	Type 416, Annealed and Centerless Ground	1 1/2	6.01
Stainless Steel	Type 416, Annealed and Centerless Ground	1 9/16	6.52
Stainless Steel	Type 416, Annealed and Centerless Ground	1 5/8	7.05
Stainless Steel	Type 416, Annealed and Centerless Ground	1 11/16	7.60
Stainless Steel	Type 416, Annealed and Centerless Ground	1 3/4	8.18
Stainless Steel	Type 416, Annealed and Centerless Ground	1 13/16	8.77
Stainless Steel	Type 416, Annealed and Centerless Ground	1 7/8	9.39
Stainless Steel	Type 416, Annealed and Centerless Ground	1 15/16	10.02
Stainless Steel	Type 416, Annealed and Centerless Ground	2	10.68
Stainless Steel	Type 416, Annealed and Centerless Ground	2 1/8	12.06
Stainless Steel	Type 416, Annealed and Centerless Ground	2 3/16	12.78
Stainless Steel	Type 416, Annealed and Centerless Ground	2 1/4	13.52
Stainless Steel	Type 416, Annealed and Centerless Ground	2 3/8	15.06
Stainless Steel	Type 416, Annealed and Centerless Ground	2 1/2	16.69
Stainless Steel	Type 416, Annealed and Centerless Ground	2 5/8	18.40
Stainless Steel	Type 416, Annealed and Centerless Ground	2 7/8	22.07
Stainless Steel	Type 416, Annealed and Centerless Ground	3	24.03
Stainless Steel	Type 416, Annealed and Centerless Ground	3 1/4	28.21
Stainless Steel	Type 416, Annealed and Centerless Ground	3 1/2	32.71
Stainless Steel	Type 416, Annealed and Centerless Ground	3 3/4	37.55

Stainless Steel	Type 416, Annealed and Centerless Ground	4	42.73
Stainless Steel	Type 416, Annealed and Centerless Ground	4 1/2	54.08
Stainless Steel	Type 416, Annealed and Centerless Ground	5	66.76
Stainless Steel	Type 416, Annealed and Cold Drawn	1/8	.042
Stainless Steel	Type 416, Annealed and Cold Drawn	5/32	.065
Stainless Steel	Type 416, Annealed and Cold Drawn	3/16	.094
Stainless Steel	Type 416, Annealed and Cold Drawn	7/32	.128
Stainless Steel	Type 416, Annealed and Cold Drawn	1/4	.167
Stainless Steel	Type 416, Annealed and Cold Drawn	9/32	.211
Stainless Steel	Type 416, Annealed and Cold Drawn	5/16	.261
Stainless Steel	Type 416, Annealed and Cold Drawn	11/32	.316
Stainless Steel	Type 416, Annealed and Cold Drawn	3/8	.376
Stainless Steel	Type 416, Annealed and Cold Drawn	13/32	.441
Stainless Steel	Type 416, Annealed and Cold Drawn	7/16	.511
Stainless Steel	Type 416, Annealed and Cold Drawn	15/32	.587
Stainless Steel	Type 416, Annealed and Cold Drawn	1/2	.668

Rounds, Steel

<i>MATERIAL</i>	<i>GRADE</i>	<i>TYPE</i>	<i>SIZE (In Inches)</i>	<i>WEIGHT/FT (Pounds per Foot)</i>	<i>BAR WEIGHT (Pounds per 20' Bar)</i>	<i>BAR WEIGHT (Pounds per 12' Bar)</i>
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1/2	.6676	13.35	
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	5/8	1.043	20.86	
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3/4	1.502	30.04	

Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	7/8	2.045	40.90
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1	2.670	53.40
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1 1/8	3.380	67.60
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1 1/4	4.173	83.46
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1 1/2	6.008	120.2
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1 5/8	7.052	141.00
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1 3/4	8.178	163.60
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2	10.68	213.60
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2 1/8	12.06	241.20
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2 1/4	13.52	270.40
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2 1/2	16.69	333.80
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2 5/8	18.40	368.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2 3/4	20.19	403.8
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2 7/8	22.07	441.40
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3	24.03	480.6
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3 1/8	26.08	521.60
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3 1/4	28.21	564.20
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3 3/8	30.42	608.40
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3 1/2	32.71	654.20
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3 5/8	35.09	654.2
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3 3/4	32.71	751.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3 7/8	40.10	802.0

Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	4	42.73	854.6
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	4 1/8	45.44	908.8
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	4 1/4	48.23	964.6
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	4 3/8	51.11	1022.2
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	4 1/2	54.08	1081.6
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	4 5/8	57.12	1142.4
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	4 3/4	60.25	1205.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	5	66.76	1335.2
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	5 1/4	73.60	1472.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	5 1/2	80.78	1615.6
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	5 3/4	88.29	1765.8
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	6	96.13	1922.6
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	6 1/4	104.3	2086.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	6 3/4	121.7	2434.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	7	130.8	2616.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	7 1/4	140.4	2808.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	7 1/2	150.2	3004.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	7 3/4	160.4	3208.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	8	170.9	3418.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	8 1/4	181.8	3636.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	8 1/2	192.9	3858.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	8 3/4	204.5	4090.0

Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	9	216.3	4326.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	9 1/2	241.0	4820.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	9 3/4	253.9	5078.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	10	267.0	5340.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	10 1/2	294.4	5888.0
Carbon Steel	1018--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	11	323.0	6460.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3/8	.3755	7.510
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1/2	.6676	13.35
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	9/16	.8449	16.90
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	5/8	1.043	20.86
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3/4	1.502	30.04
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	7/8	2.045	40.90
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1	2.670	53.40
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1 1/8	3.380	67.60
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1 1/4	4.173	83.46
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1 5/16	4.600	92.00
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1 3/8	5.049	101.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1 1/2	6.008	120.2
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1 5/8	7.052	141.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1 3/4	8.178	163.6
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	1 7/8	9.388	187.8
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2	10.68	213.6

Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2 1/8	12.06	241.2
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2 1/4	13.52	270.4
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2 3/8	15.06	301.2
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2 1/2	16.69	333.8
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2 5/8	18.40	368.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2 3/4	20.19	403.8
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	2 7/8	22.07	441.4
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3	24.03	480.6
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3 1/8	26.08	521.6
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3 1/4	28.21	564.2
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3 3/8	30.42	608.4
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3 1/2	32.71	654.2
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3 5/8	35.09	654.2
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3 3/4	32.71	751.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	3 7/8	40.10	802.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	4	42.73	854.6
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	4 1/8	45.44	908.8
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	4 1/4	48.23	964.6
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	4 3/8	51.11	1022.2
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	4 1/2	54.08	1081.6
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	4 5/8	57.12	1142.4
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	4 3/4	60.25	1205.0

Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	5	66.76	1335.2
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	5 1/4	73.60	1472.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	5 1/2	80.78	1615.6
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	5 3/4	88.29	1765.8
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	6	96.13	1922.6
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	6 1/8	100.2	2004.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	6 1/4	104.3	2086.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	6 3/4	121.7	2434.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	7	130.8	2616.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	7 1/4	140.4	2808.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	7 1/2	150.2	3004.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	7 3/4	160.4	3208.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	8	170.9	3418.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	8 1/4	181.8	3636.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	8 1/2	192.9	3858.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	8 3/4	204.5	4090.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	9	216.3	4326.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	9 1/2	241.0	4820.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	9 3/4	253.9	5078.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	10	267.0	5340.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	10 1/2	294.4	5888.0
Carbon Steel	1045--SPECIAL QUALITY--A.S.T.M. A 576	Hot Rolled	11	323.0	6460.0

Carbon Steel	A.S.T.M. A-36	Hot Rolled	1/4	.1669	3.338
Carbon Steel	A.S.T.M. A-36	Hot Rolled	5/16	.2608	5.216
Carbon Steel	A.S.T.M. A-36	Hot Rolled	3/8	.3755	7.510
Carbon Steel	A.S.T.M. A-36	Hot Rolled	7/16	.5111	10.22
Carbon Steel	A.S.T.M. A-36	Hot Rolled	1/2	.6676	13.35
Carbon Steel	A.S.T.M. A-36	Hot Rolled	9/16	.8449	16.90
Carbon Steel	A.S.T.M. A-36	Hot Rolled	5/8	1.043	20.86
Carbon Steel	A.S.T.M. A-36	Hot Rolled	3/4	1.502	30.04
Carbon Steel	A.S.T.M. A-36	Hot Rolled	7/8	2.045	40.90
Carbon Steel	A.S.T.M. A-36	Hot Rolled	15/16	2.347	46.94
Carbon Steel	A.S.T.M. A-36	Hot Rolled	1	2.670	53.40
Carbon Steel	A.S.T.M. A-36	Hot Rolled	1 1/8	3.380	67.60
Carbon Steel	A.S.T.M. A-36	Hot Rolled	1 1/4	4.173	83.46
Carbon Steel	A.S.T.M. A-36	Hot Rolled	1 5/16	4.600	92.00
Carbon Steel	A.S.T.M. A-36	Hot Rolled	1 3/8	5.049	101.0
Carbon Steel	A.S.T.M. A-36	Hot Rolled	1 1/2	6.008	120.2
Carbon Steel	A.S.T.M. A-36	Hot Rolled	1 5/8	7.052	141.00
Carbon Steel	A.S.T.M. A-36	Hot Rolled	1 3/4	8.178	163.60
Carbon Steel	A.S.T.M. A-36	Hot Rolled	1 7/8	9.388	187.80
Carbon Steel	A.S.T.M. A-36	Hot Rolled	2	10.68	213.60
Carbon Steel	A.S.T.M. A-36	Hot Rolled	2 1/8	12.06	241.20
Carbon Steel	A.S.T.M. A-36	Hot Rolled	2 1/4	13.52	270.40

Carbon Steel	A.S.T.M. A-36	Hot Rolled	2 3/8	15.06	301.20
Carbon Steel	A.S.T.M. A-36	Hot Rolled	2 1/2	16.69	333.80
Carbon Steel	A.S.T.M. A-36	Hot Rolled	2 5/8	18.40	368.0
Carbon Steel	A.S.T.M. A-36	Hot Rolled	2 3/4	20.19	403.8
Carbon Steel	A.S.T.M. A-36	Hot Rolled	2 7/8	22.07	441.40
Carbon Steel	A.S.T.M. A-36	Hot Rolled	3	24.03	480.6
Carbon Steel	A.S.T.M. A-36	Hot Rolled	3 1/4	28.21	564.20
Carbon Steel	A.S.T.M. A-36	Hot Rolled	3 1/2	32.71	654.20
